



HAL
open science

Using Pressure to Provoke the Structural Transition of Metal–Organic Frameworks

Isabelle Beurroies, Mohammed Boulhout, Philip L. Llewellyn, Bogdan Kuchta, Gérard Féray, Christian Serre, Renaud Denoyel

► **To cite this version:**

Isabelle Beurroies, Mohammed Boulhout, Philip L. Llewellyn, Bogdan Kuchta, Gérard Féray, et al.. Using Pressure to Provoke the Structural Transition of Metal–Organic Frameworks. *Angewandte Chemie International Edition*, 2010, 10.1002/anie.201003048 . hal-01465940

HAL Id: hal-01465940

<https://amu.hal.science/hal-01465940>

Submitted on 15 Feb 2017

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Using pressure to provoke the structural transition of MOF materials

Isabelle Beurroies, Mohammed Boulhout, Philip L. Llewellyn, Bogdan Kuchta, Gérard Férey, Christian Serre, Renaud Denoyel*

((Dedication----optional))

Easy and efficient energy storage is one of the problems treated by numerous researchers today. Hydrophobic nanoporous materials can potentially be used as actuators, but also as molecular springs, dampers or shock absorbers.^[1] Here, the reversible intrusion of a liquid in non-wetting pores at high pressure, with eventually a hysteresis is used to store or produce mechanical work. In the present paper we show the possibility to store mechanical energy using porous Metal Organic Framework materials (MOFs) in which their flexibility is used instead of non-wetting properties. Indeed, MOFs have found increasing interest over the past few years in potential applications such as gas separation and storage,^[2-4] liquid phase separation,^[5] or drug delivery.^[6] One of the unique properties of some of these materials is their high degree of framework flexibility which has reached 230% in the case of the MIL-88 series (MIL stands for Materials from Institut Lavoisier). In most cases, the flexibility of these materials has been induced by adsorption of guest species,^[6] which produce various types of flexibility.^[8-9] One of the most interesting classes of flexible solids are those of the MIL-53 series. These are metal(III) terephthalates built up from chains of corner sharing metal(III) octahedral (M=Al, Cr, Fe, Ga, In...) and terephthalate groups that delimit one dimensional microporous pore system.^[2] The Al and Cr forms are found in the large pore (LP) form after thermal removal of the guest species while in the presence of various different fluids, a narrow pore (NP) form is observed (MIL-53(Cr) NP; space group C2/c; $V \sim 1020 \text{ \AA}^3$) before a re-expansion to the LP form (MIL-53(Cr) LP; space group Imcm; $V \sim 1490 \text{ \AA}^3$) (Figure 1). In the case of MIL-53(Al), this reversible flexible character has also been observed as being dependent on the temperature,^[10] with a hysteresis between cooling and heating. The transition from LP to NP occurs on cooling in the 125-150K range whereas that from NP to LP occurs on heating in the range 325-375K. The presence of these different crystalline states opens the possibility for phase diagrams to be established. Whilst the previous gas adsorption studies have been carried out under various pressures,^[4,5,9] to the best of our knowledge, the response of these materials solely under pressure, without any adsorption effect in pores, has not been reported to date. In the recent study of Moggach et al, ZIF-8 samples were submitted to a high hydrostatic pressure that provokes crystal phase transitions, but with the presence of liquid inside pores.^[11] Logically, one would expect that a transition from the LP to the NP phase would occur provided a high enough pressure is applied to the MOF phase in question. One reason for this is that the MIL-53 phases are usually synthesised in the form of micrometer sized particles and it is not

easy to impose a mechanical stress around the particle in a controlled manner. However, the use of mercury porosimetry permits an isostatic pressure around the MIL-53 particles to be created. Indeed, mercury intrusion is often used to characterise the porosity of solids as the mercury is most often non-wetting and a significant pressure is required for it to penetrate the pores of a solid. One often assumes a value for the contact angle, usually in the range $130-140^\circ$ allowing the pore size and pore volume to be derived from the intrusion curve applying the Laplace-Washburn equation. In the usual intrusion pressure range, 0-400 MPa, the screened pore size ranges from around $300\mu\text{m}$ to 3nm. Thus, mercury cannot penetrate micropores such as those usually present in many MOF materials. A problem often encountered with mercury porosimetry is the compressibility of the material or the possible destruction of the pore structure that both lead to an apparent intruded volume that does not correspond to any real porosity. In the case of flexible microporous MOF materials, these technical drawbacks can be an advantage with the possibility to observe a response with pressure for systems which apparently shrink. Finally, is it possible by this technique to show that the LP to NP transition can be observed simply by applying a mechanical pressure? In the present case with MIL-53(Cr), the result from mercury porosimetry experiment is given in Figure 1 where two intrusion-extrusion cycles are performed




Figure 1. Intrusion-extrusion of mercury in MIL-53 (Cr) sample: cumulative intruded volume versus applied pressure. The arrows show the steps that correspond to the LP to NP transition. Squares: first intrusion-extrusion cycle. Triangles: second intrusion-extrusion cycle.

At a first glance, this result is a classical one that could be observed with mesoporous solids in the form of powder. In the initial pressure range to 1 MPa, the gradual intruded volume corresponds to the compactibility of the particle bed with pressure.^[12] Between 1 and 3 MPa the large increase in volume corresponds to the intrusion of mercury between particles. The second step which occurs at around 55MPa could be at first sight attributed to intrusion into mesopores, with a corresponding pore size of around 23 nm, if usual values of the contact angle are applied. However, since such a pore size is not observed from other pore size measurements such as nitrogen adsorption at 77K^[12] in which a pure Type I isotherm is observed, which is characteristic of microporosity (see SI of reference 12). Therefore, this step in the mercury intrusion experiment can be interpreted solely by the transition from the LP phase to the NP

[*] Isabelle Beurroies, Mohammed Boulhout, Philip L. Llewellyn, Bogdan Kuchta, Renaud Denoyel
Laboratoire Chimie Provence (UMR6264), CNRS-
Université Aix-Marseille I,II,III, Marseille, France
Fax: (+33)491637127
E-mail: renaud.denoyel@univ-provence.fr
Gérard Férey, Christian Serre
Institut Lavoisier(UMR CNRS 8180), Versailles, France

[**] M. Boulhout thanks the FP7 European Integrated Project „Macademia“ for financial support.



phase in which the decrease in cell volume (logically 1490 \AA^3 to 1020 \AA^3) leads to the apparent intrusion volume. As shown in Figure 1, this transition is reversible and accompanied by a hysteresis, as also observed in the temperature induced transition.^[13] A second intrusion-extrusion cycle follows the same pathway. This hysteresis shows the presence of an energetic barrier between the two phases.

A simple model may interpret the mechanism of the structural ‘breathing’ transition in MOF MIL-53 and similar structures. Most of the studies published so far focus on structural and energy characterization (by calorimetry, force field-based calculations and DFT) and a general thermodynamic interpretation. However, there is no general analysis of the competing energetic and entropic factors defining the mechanism of the transformation within the MOF structure itself. In the simple model proposed here, two energetic contributions are considered: one due to the deformation of the bond angles and the other due to the distance between ligands. They both vary during breathing of the structure. The flexibility of the structure is restricted to the connection between the inorganic chain and the carboxylic function of the terephthalate.^[14] Its two oxygen atoms are covalently bound to carbon but are linked to chromium via ionocovalent bonds. This allows a possible rotation around the O–O axis of the two planes O–Cr–Cr–O and O–C–O. The dihedral angle between these two planes is $\sim 180^\circ$ for the open structure (LP) and $\sim 140^\circ$ for the closed one (NP). The corresponding deformation energy constitutes a first energetic factor: the energy of the crystal increases when the bonds are deformed. This energy, which stabilizes the open structure, may be represented here by a deformation of dihedral energy term that depends on an energetic parameter V :

$$E_{dih} = (V/2) * (1 + \cos(180 - 2\phi)) \quad (1)$$

$180 - \phi$ represents the dihedral angle between two planes: O–Cr–Cr–O and O–C–O. The term has a minimum for $\phi = 0$. All energies are calculated with respect to this state ($E_{dih} = 0$). This potential flexibility may be activated by the presence of inserted species in the channels by the creation of weak bonds due to physisorption between the guest and the skeleton but it is easy to imagine that it can also be induced by mechanical (pressure) factors. This in turn will activate the second energetic factor which is due to the attractive interaction between the benzene rings: the energy of the crystal decreases when the distance between the rings decreases and thus stabilizes the narrow pore structure. This energy may be represented by a typical Lenard-Jones (6-12) function:

$$E_{disp} = 4\varepsilon * [(\sigma/r)^{12} - (\sigma/r)^6] \quad (2)$$

where ε is the energetic parameter (depth of the potential well) and σ the size parameter (distance of approach between molecules). The distance r is measured between the centres of the benzene rings. It depends also on the angle ϕ . This angle will thus be used as an order parameter that characterizes the transition. In reality, the distance dependence may be different than the one deduced from the (6-12) function representation. Different combinations (n,m) of the power parameters have been tested but they do not change the qualitative behaviour presented below. This problem will be addressed in future studies where the transition will be modelled and analyzed using a quantitative approach. The competition between the two energy terms stabilizes one or the other phase with an energy barrier between them. This leads to a hysteresis when one phase is being transformed into the other one, as observed experimentally. In Figure 2 the energy $E_{dih} + E_{disp}$ is plotted versus the angle ϕ . Quantitative estimations have been made using the dihedral parameter from *ab initio* calculations ($V = 20 \text{ kJ/mol}$).^[15] Entropy is not included in our qualitative model. The influence of the different strengths of the dispersive energy have been studied parametrically for different values of the V/ε ratio leading to two main conclusions: i) the relative strengths of the energy terms (characterized by V/ε) will affect the relative stability of the phases, that is, the pressure and/or temperature of transition and ii) the barrier between the phases (indicated in the Figure 2 as TS – Transition State) changes for different values of V/ε and affects the energy required to transform one phase into another. Obviously, the

dispersive interactions between the ligands are not high enough as compared to the dihedral energy to stabilize the NP phase but the energy provided by pressure may induce the transition to this less stable state.




Figure 2. $E = E_{dih} + E_{disp}$ as a function of the dihedral angle ϕ for different V/ε ratios. The minimum at $\phi=0$ represents the open structure LP, the other minimum represents the NP structure. There is a barrier (Transition State) between the minima indicated as TS. Losange: $V/\varepsilon=1.7$. Squares: $V/\varepsilon=2.5$. Triangles: $V/\varepsilon=4$. Circles: $V/\varepsilon=5$.

During the isostatic compression experiment, the only work (W) provided to the system is mechanical. One can then write the free energy variation (ΔF) of the system during the isothermal transition as $\Delta F = W$ with:

$$W = \int_{V_2}^{V_3} P dV \quad (3)$$

which is the work of the pressure forces during the step corresponding to the transition. V_2 and V_3 are defined in Figure 2. ($V_3 - V_2$) is the variation of volume undergone by the material during the transition from one state to the other. This work is in fact used to overcome the energetic barrier represented in Figure 2. It is larger than the one needed to reach the NP form along a reversible path. The excess of energy is dissipated in the form of heat which is not measured in the present experiment. Consequently the free energy variation between the two phases calculated by applying Equation 3 to the experimental data is an upper estimation. Calculating this variation with present data a value of 14 J g^{-1} is obtained. Assuming that the molar mass of dried MIL-53 (Cr) is 233 g.mol^{-1} ,^[13] a value of 3.5 kJ mol^{-1} is obtained for the transition free energy, in reasonable agreement with the range of calculated values shown in Figure 2. This is also in the range of the values ($2\text{-}6 \text{ kJ.mol}^{-1}$) obtained by Coudert et al^[16] who proposed a thermodynamic analysis of various host-guests systems which includes the free energy of this transition, whereas 5 kJ.mol^{-1} where obtained in an indirect manner from DSC measurements of the dehydration energy.^[17] This is slightly smaller than the published value issued from DFT and force-field calculations:^[15] 30 kJ per unit cell or 7 kJ.mol^{-1} , as one unit cell contains 4 Cr atoms. From mercury porosimetry, the density of the material is also obtained at the end of the intrusion branch: it then corresponds to the apparent density of the narrow pore form. A value of 1.59 mL/g is obtained which is very close the theoretical value of 1.65 mL/g .^[13] The variation of volume between LP and NP forms at the transition pressure is around $0.25 \text{ cm}^3 \text{ g}^{-1}$ which is close to the value deduced from the structural studies. Indeed, $0.3 \text{ cm}^3 \text{ g}^{-1}$ is derived from the difference between the unit cell volumes of the LP and NP forms.^[13] The difference between these two values may arise from an already slightly compressed LP phase at the transition pressure.

From a fundamental point of view, this study shows that the mechanical properties of flexible MOF materials can be studied directly using mercury porosimetry. The modulation of an external pressure can lead to energetic and volumetric information on the

flexibility of MOF systems. It also shows that these systems may be potentially used in mechanical energy storage type applications based on a much simpler approach from the one using non-wetting porous materials.^[1] Furthermore, the energy absorbed in a cycle of intrusion-extrusion, calculated by integration of Equation 3 along a full cycle, is around 12J.g⁻¹, which is larger than the one which can be stored with mesoporous hydrophobic solids.^[18,19] Moreover, the simple model used here to explain the observed behaviour opens the prospects that by varying the nature of metal centers and ligands, different energetic behaviours could be obtained. This will allow a modulation of the storage capabilities and the manufacturing of either dampers (transition with hysteresis) or molecular springs (transition without hysteresis).

Experimental Section

The MIL-53(CR) sample was synthesised following the already published procedure^[8]. The nitrogen adsorption at 77K (results not shown) was carried out with an ASAP2010 apparatus from Micromeritics. The sample was outgassed overnight at 200°C under a residual pressure lower than 1Pa. Mercury intrusion-extrusion experiment was carried out with the Autopore 9220 apparatus from Micromeritics. In order to start the experiment with the open structure, a special treatment method was used because it is not possible to heat the sample in-situ with mercury porosimeters. The sample was immersed in methanol which is known to open the structure. Then it was outgassed at 150°C, cooled and transferred as soon as possible in the mercury porosimetry cell for analysis. In the mercury apparatus, a primary vacuum is realised (lower than 5Pa).

Received: ((will be filled in by the editorial staff))
Published online on ((will be filled in by the editorial staff))

Keywords: mercury porosimetry · metal organic framework · energy storage · nanospring · hysteresis

-
- [1] V. Eroshenko, R.-C. Regis, M. Soulard, J. Patarin, *J. Am. Chem. Soc.* **2001**, *123*, 8129-8130
[2] G. Férey, *Chem. Soc. Rev.* **2008**, *37*(1), 191-214. .

-
- [3] M. Latroche, S. Surblé, C. Serre, C. Mellot-Draznieks, P.L. Llewellyn, J.-H. Lee, J.-S. Chang, S. H. Jhun, G. Férey, *Angew. Chem., Int. Ed.* **2006**, *45*, 8227- 8231
[4] S. Bourrelly, P.L. Llewellyn, C. Serre, F. Millange, T. Loiseau, G. Férey, *J. Am. Chem. Soc.* **2005**, *127*, 13519-13521.
[5] L. Alaerts, C. E. A. Kirshhock, M. Maes, M. A. van der Veen, V. Finsy, A. Depla, J. A. Martens, G. V. Baron, P. A. Jacobs, J. F. M. Denayer, D. E. De Vos, *Angew. Chem., Int. Ed.* **2007**, *46*, 4293-4297.
[6] P. Horcajada, T. Chalati, C. Serre, B. Gillet, C. Sebrie, T. Baati, J.F. Eubank, E. Heurtaux, P. Clayette, C. Kreuz, J.-S. Chang, Y.K. Hwang, V. Marsaud, P.-N. Bories, L. Cynober, S. Gil, G. Férey, P. Couvreur, R. G. Férey, *Nature. Mater.*, **2010**, *9*, 172-178.
[7] Hirofumi Kanoh et al., *J. Colloid Interface Sci.*, **2009**, *334*, 1-7.
[8] F. Millange, C. Serre, N. Guillou, G. Férey, R.I. Walton, *Angew. Chem. Int. Ed.*, **2008**, *47*, 4100-4105.
[9] P. L. Llewellyn, P. Horcajada, G. Maurin, T. Devic, N. Rosenbach, S. Bourrelly, C. Serre, D. Vincent, S. Loera-Serna, Y. Filinchuk, G. Férey, *J. Am. Chem.Soc.* **2009**, *131*, 13002-13008.
[10] Y.Liu, J.-H. Her, A. Dailly, J. Ramirez-Cuesta, D.A. Neumann, C.M. Brown, *J. Am. Chem. Soc.*, **2008**, *130*, 11813-11818.
[11] S.A. Moggah, T.D. Bennet and A. Cheetham, *Angew. Chem., Int. Ed.*, **2009**, *48*, 7087-7089.
[12] H. Giesche, *Part. Part. Syst. Char.*, **2006**, *23*, 9-19.
[13] C. Serre, F. Millange, C. Thouvenot, M. Nogues, G. Marsolier, D. Louër, G. Férey, *J. Am. Chem. Soc.*, **2002**, *124*, 13519-13526.
[14] G. Férey and C. Serre, *Chem. Soc. Rev.*, **2009**, *38*, 1380-1399.
[15] D. S. Coombes, F. Cora, C. Mellot-Draznieks, and R. G. Bell, *J. Phys. Chem. C*, **2009**, *113*, 544-552.
[16] F.-X. Coudert, M. Jeffroy, A.H. Fuchs, A. Boutin and C. Mellot-Draznieks, *J. Am. Chem. Soc.*, **2008**, *130*, 14294-14302.
[17] S. Devautour-Vinot, G. Maurin, F. Henn, C. Serre, T. Devic, G. Férey, *Chem.Comm.*, **2009**, 2733-2735.
[18] L. Coiffard, V. Eroshenko, J.-P. Grolier, *AIChE J.*, **2005**, *51*, 1246-1257
[19] B. Lefevre, A. Saugey, J.L. Barrat, L. Bocquet, E. Charlaix, P.F. Gobin, G. Vigier, *J. Chem. Phys.*, **2004**, *120*, 4927-4938
...


Entry for the Table of Contents (Please choose one layout)

Layout 1:

Metal-Organic Frameworks

Isabelle Beurroies, Mohammed Boulhout, Philip L. Llewellyn, Bogdan Kuchta, Gérard Férey, Christian Serre, Renaud Denoyel* **Page – Page**

Using pressure to provoke the structural transition of MOF materials



A hysteresis of intrusion-extrusion of mercury in MIL 53 (Cr) particles is observed that cannot be due to the presence of mesopores in this purely microporous material. It is interpreted by the transition from large pore to narrow pore forms of this MOF material which is here provoked by the isostatic pressure created by mercury around the porous particles. The observed behavior may be qualitatively explained by a simple energetic model and opens possibilities for applications as dampers or molecular spring.

Layout 2:

((Catch Phrase))

((Author(s), Corresponding Author(s)*))
_____ **Page – Page**

((TOC Graphic))

((Title Text))

((Text for Table of Contents, max. 450 characters))