



**HAL**  
open science

## Nanohybrids as a tool to control the dispersion of organic emitters in solution-processed electroluminescent layers

Jonathan Phelipot, Payal Manzhi, Nicolas Ledos, Denis Tondelier, Bernard Geffroy, Pierre- Antoine Bouit, Jörg Ackermann, Muriel Hissler, Olivier Margeat

### ► To cite this version:

Jonathan Phelipot, Payal Manzhi, Nicolas Ledos, Denis Tondelier, Bernard Geffroy, et al.. Nanohybrids as a tool to control the dispersion of organic emitters in solution-processed electroluminescent layers. *New Journal of Chemistry*, 2022, 46 (47), pp.22574-22580. 10.1039/D2NJ05016A . hal-03840466

**HAL Id: hal-03840466**

**<https://amu.hal.science/hal-03840466v1>**

Submitted on 5 Nov 2022

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

## ARTICLE

## Nanohybrids as a tool to control the dispersion of organic emitters in solution-processed electroluminescent layers

Jonathan Phelipot,<sup>a</sup> Payal Manzhir,<sup>b,c</sup> Nicolas Ledos,<sup>d</sup> Denis Tondelier,<sup>c</sup> Bernard Geffroy,<sup>b,c</sup> Pierre-Antoine Bouit,<sup>d</sup> Jörg Ackermann,<sup>a</sup> Muriel Hissler,<sup>d,\*</sup> Olivier Margeat.<sup>a,\*</sup>

Received 00th January 20xx,  
Accepted 00th January 20xx

DOI: 10.1039/x0xx00000x

Fluorescent organic-inorganic nanohybrids based on  $\pi$ -extended hydroxyoxophosphole emitters grafted onto ZnO nanocrystals, have been introduced as an efficient way to control the spatial arrangement of the organic emitters within a host material. The homogeneous dispersion of the emissive nanohybrids within a host matrix is achieved *via* co-grafting of an additional surfactant, leading to very smooth films with low roughness. Interestingly, the co-grafting of this surfactant not only improves the thin film morphology but also enhances its photoluminescence quantum yield and allows for the easy solution-processing of this material as an emissive layer in a simplified OLED structure. These devices display strongly improved performances, by more than one order of magnitude, compared to OLEDs using pure nanohybrids. These promising results prove the potential of this technique to graft any type of luminophore in efficient solution-processed light-emitting devices.

### Introduction

Research efforts on organic light-emitting diodes (OLEDs) have demonstrated practical applications in nowadays flat panel displays thanks to their advantages of flexibility, fast response, high stability or light weight.<sup>1–4</sup> In this context, a great variety of emitters that have been used are either molecular (from fluorescent or thermally-activated delayed fluorescent [TADF] organic luminophores to phosphorescent transition metal complexes),<sup>5</sup> macromolecular (fluorescent polymers)<sup>6</sup> or hybrid organic/inorganic (QD-LEDs).<sup>7</sup> So far, most multilayered OLED products are still fabricated by vacuum deposition technologies that require high running cost.<sup>8–12</sup> The need for cost-effective OLED products drives considerable developments to reach innovative materials and fabrication techniques suitable for low-cost and large-area manufacturability of OLEDs. In this respect, solution-process techniques, such as spin coating, blade coating, roll-to-roll or ink-jet printing, show great potential in achieving these goals.<sup>13,14</sup> As one of the key materials, highly-efficient solution-processable emitting materials are essential for printed OLEDs. To achieve such

property, the emitters (either fluorescent, phosphorescent or TADF) are generally dispersed as guests in suitable concentrations into host materials displaying favorable morphological properties.<sup>15</sup> The appropriate guest-host combination selection plays a key role in determining the emissive characteristics in the film state to avoid either morphological inhomogeneities or detrimental emitter-emitter interactions (such as triplet-triplet annihilation). However, solution-processing of host-guest-doped OLEDs faces well-known phase separation problem, inducing serious aggregation of the molecules and resulting in emission quenching.<sup>16,17</sup> Although some specific approaches have shown how to avoid this problem,<sup>18,19</sup> controlling the dispersion of organic emitters in a host material by solution approach remains a key challenge in the field. Indeed, a tool to control the emitters' arrangement in the host material would allow for the unrestricted use of all promising types of luminophores.

We recently showed that nanohybrids made from the grafting of fluorescent organic emitters onto zinc oxide (ZnO) nanocrystals present aggregation-induced emission (AIE) effects leading to highly photoluminescent thin films.<sup>20</sup> However, the OLED devices made from pure nanohybrids displayed limited performances (luminance reaching 60 cd·m<sup>-2</sup> at 50 mA·cm<sup>-2</sup>) mainly due to a detrimental morphology of the active layer affecting the charge transport. In the present work, we show that dispersion of these nanohybrids within a polymeric host material is a promising approach to greatly enhance the performance of the OLEDs. More importantly, we demonstrate that co-grafting of the organic emitter together


<sup>a</sup> Aix Marseille Univ, CNRS, CINaM, Marseille, France..

<sup>b</sup> Laboratoire de Physique des Interfaces et des Couches Minces (LPICM), CNRS, Ecole Polytechnique, IP Paris, Palaiseau Cedex, France.

<sup>c</sup> Université Paris-Saclay, CEA, CNRS, NIMBE, LICSEN, 91191, Gif-sur-Yvette, France.

<sup>d</sup> Univ Rennes, CNRS, ISCR - UMR 6226, F-35000 Rennes, France.

† Electronic Supplementary Information (ESI) available: [details of any supplementary information available should be included here]. See DOI: 10.1039/x0xx00000x



**Figure 1.** Schemes of a) the individual fluorescent ligand **L** and nanoparticles ZnO, b) the nano hybrids **N**, and c) the emissive layers using dispersed nano hybrids within the host material with (**M:N:OA**) or w/o (**M:N**) the use of oleic acid.


with an additional surfactant is an efficient way to control the spatial arrangement of the emitters within a host material (polyvinylcarbazole with oxadiazole). Indeed, the dispersion of the emissive nano hybrids within the host matrix is controlled using classical surfactants for nanocrystals, such as oleic acid. OLEDs devices were then prepared using homogeneously dispersed nano hybrids films with greatly enhanced luminance (reaching  $1000 \text{ cd}\cdot\text{m}^{-2}$  at  $50 \text{ mA}\cdot\text{cm}^{-2}$ ) compared to the pure nano hybrids film, thus highlighting the potential of this approach.

## Design of the emissive nano hybrid layer

### Morphology control of the nano hybrid layer

To design the fluorescent nano hybrids (referred as **N**), we relied on the use of  $\pi$ -extended hydroxyoxophosphole emissive ligands (referred as **L**). Hence, we and others showed that these compounds allow to generate highly luminescent hybrid materials after grafting on inorganic substrates ( $\text{SiO}_2$ , ZnO, HgS).<sup>20–22</sup> Here, according to our reported strategy, **L** is grafted in solution onto the surface of 6 nm large ZnO nanoparticles (**Figure 1a/b**). As previously shown, the resulting nano hybrids present aggregation-induced emission (AIE) after grafting of the ligand **L**, explaining the change from low emissive solution to highly emissive solid state.<sup>20</sup> In our previous work, the solution-processing of electroluminescent layers based on pure nano hybrids films lead to OLEDs with limited device performance due to morphology inhomogeneities which strongly affected the charge transport as well as the reproducibility of the devices. Indeed, rough layers were obtained, due to undesirable aggregates causing electrical short-circuits and non-homogeneous light emission. To improve both charge transport properties and morphology of the emissive layer, we decided to use classical host/guest structure,<sup>23</sup> through the incorporation of the nano hybrids as guest emitters within a host matrix **M**, leading to a layer referred as **M:N** as depicted on **Figure 1c**. The association of the


polymer polyvinylcarbazole (PVK) with an oxadiazole derivative (OXA) was chosen as host matrix for the nano hybrids. Indeed, it has been reported that PVK, associated to oxadiazole or carbazole derivatives to ensure the electron transport, is an excellent candidate to host wide types of fluorescent or phosphorescent emitters.<sup>24,25</sup> The incorporation of nanoparticles with diameter about 5 nm to more than 100 nm within this polymer as host matrix has also been reported.<sup>26</sup> Moreover, many studies on the influence of the guest concentration were done, which is a key parameter for the OLED device performances.<sup>26,27</sup>



**Figure 2.** a) Scheme of the floating-layer technique used for depositing film on the holey carbon coated TEM grid. b-c) TEM images of the layer **M:N<sub>10</sub>** at two magnifications. d-e) TEM images of the layer **M:N<sub>10</sub>:OA** at two magnifications.

To investigate the morphology of the layer and evaluate the aggregation of the nanohybrids within the host, Transmission Electron Microscopy (TEM) was employed. For sample preparation, a modification of the floating-layer technique was applied.<sup>28</sup> First, sacrificial PEDOT:PSS was coated on a substrate before the spin coating of **M:N** emissive layer on top. After a brief annealing to dry the layers, the PEDOT:PSS film was dissolved in deionized water. Floating thin films of the emissive layer were then recovered and deposited on a holey carbon-coated TEM grid, as shown in **Figure 2a**. The emissive layer presented in the following part is referred as **M:N<sub>10</sub>** sample, using a solution containing 10% w/w of nanohybrids with respect to the host matrix. The resulting TEM images are represented in **Figure 2b/c** at two different magnifications. From the large area in **Figure 2b**, the layer **M:N<sub>10</sub>** reveals nanohybrid aggregates over a micron scale, highlighted on the picture by the white-dotted circles. The presence of high amounts of aggregated nanohybrid structures is confirmed in **Figure 2c**, proving the low ability of the nanohybrids to be homogeneously dispersed within the host matrix. These undesirable aggregates generate electrical short-circuits and therefore need to be removed to obtain functional and reproducible OLED devices. For this purpose, to avoid the agglomerate formation and improve the homogeneous dispersion of the nanohybrids within the host, a low amount of surfactant was used as additive to the **M:N<sub>10</sub>** solution. In this respect, oleic acid (OA), a classical surfactant for the dispersion of nanocrystals in solution, was chosen.<sup>29</sup>

The layer referred as **M:N<sub>10</sub>:OA** corresponds to the blend including the OA treatment in solution (addition of 0.2% v/v). The resulting TEM images are represented in **Figure 2d/e** at two different magnifications. Interestingly, the **M:N<sub>10</sub>:OA** layer morphology is totally different from the one obtained with **M:N<sub>10</sub>**. Even if slightly more dense areas composed of nanohybrids are noticeable, no aggregate can be found over the whole layer. The OA treatment appears as an efficient method to avoid the formation of aggregates and to ensure the homogeneous dispersion of the nanohybrids. Moreover, the same trends were observed when using other ratios of nanohybrids, as in the case of solutions containing 5 or 15% w/w of nanohybrids with respect to the host matrix, layers referred as **M:N<sub>5</sub>** and **M:N<sub>15</sub>**, that present the same morphology improvement using OA, i.e. **M:N<sub>5</sub>:OA** and **M:N<sub>15</sub>:OA** respectively (**Figure S1**). We also studied the impact of the concentration of OA to further improve the nanoscale morphology of **M:N<sub>10</sub>:OA** layer. It was found that employing lower amounts of OA in solution systematically leads to the formation of aggregates. On the contrary, increasing the amount of OA in the solution (from 0.2 to 0.6% v/v) does not further improve the morphology of the layer (**Figure S2**). Thus, the value of 0.2% v/v of OA appears as an optimal value to limit any excessive use of this surfactant. The morphology of the nanohybrids within the layer was also studied using Secondary-Electron Microscopy (SEM) on a cross-section of the sample (**Figure S3**) to determine the vertical dispersity of the nanohybrids. Even if the contrast is very weak, the nanohybrids appear to be present over the whole 50 nm thick layer, with



**Figure 3.** AFM images of the layer **M:N<sub>10</sub>** at 10x10µm scale (a) and 5x5µm scale (b). AFM images of the layer **M:N<sub>10</sub>:OA** at 10x10µm scale (c) and 5x5µm scale (d).


slightly more dense areas at the top of the layer, however ruling out any clear vertical segregation.

The surface morphology was further studied by Atomic Force Microscopy (AFM). AFM images performed on layers containing 10% of nanohybrids, processed with or w/o the use of OA *via* spin-coating, are presented in **Figure 3**, while the related roughness values of the layers are given in **Table 1**. In the absence of OA, **M:N<sub>10</sub>** layer surface confirms the presence of irregular nanohybrid aggregates within the host matrix, large on a micron scale and as height as 80 nm (**Figure 3a/b**). This inhomogeneous surface is characterized by a very high roughness, measured at 11.1 nm from the 10x10µm image. On the opposite, the **M:N<sub>10</sub>:OA** emissive layer presents a very smooth surface morphology, without any noticeable aggregate over the whole surface (**Figure 3c/d**), as already pointed out by the SEM cross-section image. The surface roughness is, as expected, much lower and measured at 1.1 nm from the same 10x10µm scale. The same trends were observed with the other ratios of nanohybrids (**Figure S4** and **Table 1**). The **M:N<sub>5</sub>** and **M:N<sub>15</sub>** thin films present high roughness values of 6.0 and 4.8 nm, respectively, caused by the presence of underlying aggregates. After OA addition in the solution, the roughness of the resulting thin films decreases again significantly to reach 1.4 nm (**M:N<sub>5</sub>:OA**) and 1.6 nm (**M:N<sub>15</sub>:OA**). These low roughness values are in the range of those obtained in other spin-coated guest-host films used in electroluminescent OLED devices.<sup>23,26,30</sup>

	<b>M:N<sub>5</sub></b>	<b>M:N<sub>5</sub>:OA</b>	<b>M:N<sub>10</sub></b>	<b>M:N<sub>10</sub>:OA</b>	<b>M:N<sub>15</sub></b>	<b>M:N<sub>15</sub>:OA</b>
RMS roughness (nm)	6.0 +/- 0.6	1.4 +/- 0.1	11.1 +/- 1.0	1.1 +/- 0.1	4.8 +/- 0.5	1.6 +/- 0.1

**Table 1.** Root mean square roughness obtained from 10x10µm AFM measurements of layers containing 5, 10 and 15% of nanohybrids, with or w/o the use of OA in the solution.

The use of 0.2% v/v of OA as additional surfactant appears as an efficient treatment of the host/guest solution to avoid nanohybrids aggregates and ensure the homogeneous dispersion of the nanohybrids within the matrix, leading to smooth film with low roughness, as required to elaborate reproducible and functional LED devices. The impact of this additive on the optical and electronic properties is addressed in the next paragraph.



**Figure 4.** Absorption spectra in chlorobenzene solution (a) and emission spectra ( $\lambda_{\text{ex}}=400$  nm) of the resulting films (b) of **M:L**, **M:N<sub>10</sub>** and **M:N<sub>10</sub>:OA** on glass substrate.

#### The role of OA on the luminescence properties

To determine the effect of OA on the optical properties, the absorption and emission spectra of the nanohybrids with and w/o OA addition were studied when dispersed in the host matrix (samples **M:N<sub>10</sub>** and **M:N<sub>10</sub>:OA**, respectively). As a reference, the pure emitter **L** dispersed in the host matrix is also reported (**M:L**). The main absorption band of **L** in diluted solution ( $\lambda_{\text{abs}}=400$  nm, **Figure 4a**) appears to be slightly blue-shifted after formation of the nanohybrids, as previously observed.<sup>20</sup> Indeed, the spectra of **M:N<sub>10</sub>** and **M:N<sub>10</sub>:OA** are very similar with  $\lambda_{\text{abs}}=390$  nm. However, the spectra of these two samples differs at higher wavelength ( $\lambda > 500$  nm) as, in contrast to **M:N<sub>10</sub>:OA**, the **M:N<sub>10</sub>** display light scattering signal caused by the presence of nanohybrids aggregates. The absence of light scattering from **M:N<sub>10</sub>:OA** unambiguously reveals that the OA treatment allows to homogeneously disperse the nanohybrids within the matrix. The presence of aggregates in absence of OA treatment in **M:N<sub>10</sub>** is also observed on the absorption spectra of the resulting layers (**Figure S5**).

Emission spectra were recorded on the thin films with an excitation at  $\lambda_{\text{ex}}=400$  nm, *i.e.* at the maximum absorption of the emitter **L** and thus avoiding any emission from the matrix or from ZnO nanocrystals (**Figure 4b**). The pure organic emitter in the matrix, **M:L**, presents a strong green emission ranging from 440 nm to 650 nm, as expected for the emission of this molecule alone<sup>20</sup> and showing the limited influence of the host matrix on the emission wavelength. The nanohybrids containing films **M:N<sub>10</sub>** and **M:N<sub>10</sub>:OA** both present the typical **L** emission.

To quantitatively compare these emission properties, photoluminescence quantum yields (PLQYs) were determined using an integrating sphere according to « John de Mello » method,<sup>31</sup> which is independent on the layer thickness. The

PLQYs were measured for the matrix layers containing different mass ratios of pure emitter **L** or nanohybrids **N**, with or w/o OA treatment (**Table 2**). The PLQYs for X= 5% and 10% follow the same trend, with PLQYs about 10-12% for **M:L**, being in the same range at 11-14% for **M:N** and surprisingly reaching values as high as 31-35% for **M:N:OA**. The PLQY for X= 15% starts with slightly higher values about 22-24% for **M:L<sub>15</sub>** and **M:N<sub>15</sub>** but also reaches the same high value of 33% for **M:N<sub>15</sub>:OA**. The OA

treatment clearly shows that homogeneously dispersed nanohybrids in the matrix is the key to enhance the PLQY (by a factor  $\sim 2 - 3$ ). While the OA ligands improve mainly the solubility of the nanohybrids, we address the PLQY increase in the emissive films to a higher amount of grafted emitters on the ZnO nanoparticle surface, as the overall available ZnO surface is larger due to the absence of aggregates already in solution. To understand the optical and morphological properties of the **M:N<sub>15</sub>:OA** layer more in detail, we varied OA quantity by comparing the PLQY of **M:N<sub>10</sub>:OA** layers, containing respectively 0.2%, 0.4% and 0.6% v/v of OA (**Table S1**). It was proven in the previous part that the amount of OA in **M:N:OA** has no significant impact on the surface morphology of the layer. As it can be seen in **Table S1**, the variation of the OA concentration has also no impact on the PLQY of the luminescent material. We can thus consider that with 0.2% of OA, all fluorescent ligands are already grafted at the ZnO surface, while using additional OA would have a negative impact on the charge injection or transport within the emitter film.

	Sample name	<b>M:L<sub>x</sub></b>	<b>M:N<sub>x</sub></b>	<b>M:N<sub>x</sub>:OA</b>
PLQY (%)	X= 5%	12 $\pm$ 1	11 $\pm$ 1	31 $\pm$ 3
	X= 10%	10 $\pm$ 1	14 $\pm$ 1	35 $\pm$ 3
	X= 15%	24 $\pm$ 2	22 $\pm$ 2	33 $\pm$ 3

**Table 2.** Photoluminescence quantum yields for different amounts of emitter (for **M:L**) or nanohybrids (for **M:N** and **M:N:OA**) in the host matrix.

In conclusion, the OA treatment not only helps to obtain smooth films of homogeneously dispersed nanohybrids, but also enhances the luminescence of the layers, without modifying the emission wavelength, as usually observed with


AIE luminophore. The study is completed in the following part by comparing the performances of OLED devices using **M:N:OA** based electroluminescent layer.

## OLED devices using emissive nanohybrid layer

The different nanohybrids were studied as emitting layer in simple OLED structures. The device structure (Figure 5a) consists of a classical ITO/ PEDOT:PSS/ **M:N:OA**/ BCP/ Alq<sub>3</sub>/ LiF/ Al stack with 0.3 cm<sup>2</sup> of active surface, the emitting layer **M:N:OA** being solution-processed by spin-coating (see the ESI for fabrication details). The current density–voltage–luminance (J–V–L) curves of the diodes were measured to optimize the device performances. Importantly, for all matrix compositions including nanohybrids, the electroluminescence spectrum corresponds to the photoluminescence spectrum of nanohybrids included in matrix, with a maximum emission in the green region at 520 nm (Figure 5b). The inset shows a photograph image of the diode working at 50 mA·cm<sup>-2</sup> having homogeneous emission over the whole emitting surface. As a reference, we processed diodes using only the PVK/OXA matrix as electroluminescent layer, that show only weak emission in the blue region (maximum emission at 470 nm - Figure S6), characteristic of PVK/OXA. This proves that the green emission in **M:N:OA** devices originates from the electroluminescence of

the nanohybrids. At this point, it has to be pointed out that a reference device using the incorporation of only emitter “L” as guest within the host matrix (i.e. without ZnO introduction) could not be measured. Indeed, such materials lead to very rough films, causing short-circuits in the devices.

The device optimization was first realized by varying the thickness of the electroluminescent layer **M:N:OA** between 40 nm and 100 nm (see Figure S7 and related performances in Table S2). The best performing OLEDs were obtained with emission layer of 50 nm thickness leading to EQE value of 0.71%, luminance efficiency of 1.84 cd/A and 0.82 lm/W in power efficiency. Drops of the overall performances were observed for the active layers thicker than 50 nm, with EQE of 0.34%. For the lowest thickness, at 40 nm, the threshold voltage slightly increased, but the overall performances remained close to the ones measured for the 50 nm thick device. However, in the case of this 40 nm thick layer, and only for this one, the devices degraded fast under high voltage and the reproducibility was low, which may be attributed directly to the very thin active layer. Further optimizations with other parameters were thus realized using electroluminescent layer thickness at 50 +/- 5 nm. The second set of optimizations concerned the determination of the optimal OA amount for nanohybrid preparation. The impact of the concentration of OA in **M:N:OA** layers on the



**Figure 5.** a) Scheme of the LED device structure, b) Electroluminescent spectra measured at 50 mA·cm<sup>-2</sup> (inset: photograph image of the device), c) J-V curves of the different **M:N<sub>x</sub>:OA** samples and d) Corresponding JVL curves for the best performing **M:N<sub>10</sub>:OA** sample.

X% in M:N <sub>x</sub> :OA	0 % (ref)	5 %	10 %	15 %	20 %
Threshold voltage (V)	4	6	4	8	9
EQE (%)	0.18	0.71	0.71	0.58	0.34
Power efficiency (lm/W)	0.12	0.66	0.82	0.36	0.24
Luminance efficiency (cd/A)	0.28	2.00	1.84	1.81	1.20

**Table 3.** Device performances for various amounts of nano hybrids in the electroluminescent layer M:N<sub>x</sub>:OA in ITO/PEDOT:PSS/M:N<sub>x</sub>:OA/BCP/Alq<sub>3</sub>/LiF/Al devices.

performance of the OLEDs was studied by elaborating devices with OA amount ranging from 0.05% to 0.6% v/v (see **Figure S8** and related performances in **Table S3**). This study clearly reveals that 0.2% v/v is the optimal OA concentration to obtain the best devices. Indeed, at higher OA concentrations, the overall parameters were quickly degraded, with increase of the threshold voltage from 4 V to 7 V, and drops of the EQE from 0.71% to 0.34%, power efficiency from 0.82 lm/W to 0.27 lm/W and luminance efficiency from 1.84 cd/A to 1.32 cd/A. These performance losses were attributed to the insulating behavior of the OA fatty acid at these excessive concentrations. At lower OA concentrations, the overall parameters were less affected, with even a slight increase in the luminance efficiency reaching 1.98 cd/A at 0.1% v/v of OA. However, for concentrations of OA below 0.2%, a clear degradation of the electroluminescent layer morphology was frequently observed in the devices (due to the formation of aggregates as seen in the part 2.1), clearly lowering the performance reproducibility.

In the previous parts, it was shown that the amount of nano hybrids incorporated within the matrix was not affecting the surface morphology (RMS roughness between 1.1 and 1.6 nm) neither the photoluminescence of the layer (PLQY between 33 and 35%). Such layers were all good candidates to prepare OLED devices. Electroluminescent devices were thus realized using matrices containing different mass ratios of nano hybrids (M:N<sub>x</sub>:OA samples) with ratios ranging from X= 0% (pure matrix film) to 20%, under optimized conditions *i.e.* 50 nm thick active layer and 0.2% v/v of OA (see **Figure 5c** and related performances in **Table 3**). By adding more than 10% of nano hybrids in the matrix, the threshold voltage consequently increased from 4 V to more than 9 V, together with lower EQE, power and luminescence efficiencies. This suggests that the presence of a large amount of nano hybrids negatively affects the charge injection and transport properties of the matrix. Using lower ratios of nano hybrids in M:N<sub>x</sub>:OA layers, *i.e.* 5% and 10%, the performance of the OLEDs was improved and comparably high, reaching the same EQE value of 0.71% with power efficiencies of 0.66 and 0.82 lm/W and luminance efficiencies of 2.00 and 1.84 cd/A, respectively. However, a significant lower threshold voltage of 4 V was obtained for M:N<sub>10</sub>:OA compared to 6 V measured for M:N<sub>5</sub>:OA. Thus, the best devices were obtained using M:N<sub>10</sub>:OA as electroluminescent layer. These devices reached a maximum luminance at 1000 cd.m<sup>-2</sup> at a current density of 50 mA.cm<sup>-2</sup>, as shown in **Figure 5d**. Compared to our previous work, in which an electroluminescent layer made from the pure nano hybrids led to OLEDs with a maximum luminance of only 60 cd.m<sup>-2</sup>, the

developed co-grafting technique of emissive ligand and OA ligand, in combination with the use of a host matrix, provides performance enhancement of more than one order of magnitude.

## Conclusions

Solution-processable materials for organic light-emitting diodes require emitters well-dispersed as guests into the host material. This needs homogeneous dispersion to avoid morphological inhomogeneities, aggregates, phase separation issues or detrimental emitter-emitter interactions. In this work, organic-inorganic nano hybrids were used as an efficient way to control the spatial arrangement of the organic emitters within the host material. The homogeneous dispersion of the emissive nano hybrids within the matrix appears to be assisted by the co-grafting of a surfactant such as oleic acid, leading to very smooth films with low roughness. Interestingly, we proved that the oleic acid treatment enhances the PLQY of the thin films, due to an easier emitter grafting on the better accessible nanocrystal surface in the absence of aggregates. The solution-processing of this material as emissive layer in simple OLED structure led to device with strongly improved performances, by more than one order of magnitude, compared to OLEDs using pure nano hybrids. The successful combination of grafting two ligands, one controlling the emission properties of the hybrid nanostructure and one governing the dispersion within the host matrix, into efficient nano hybrids points towards a highly versatile strategy to adapt a large pallet of organic emitters for efficient solution-processed light-emitting devices. Future work will explore the combination of the presented nano hybrids within more efficient hosts with more suitable ambipolar charge transport or using graftable emitters with improved emission properties (different colors of emission, higher PLQY or presenting TADF properties).

## Experimental section

Detailed syntheses and characterizations of all compounds, details of equipment and device elaboration are given in Supporting Information.

## Conflicts of interest

There are no conflicts to declare.

## Acknowledgements

This work is supported by the Ministère de la Recherche et de l'Enseignement Supérieur, the CNRS, the Région Bretagne (ARED grant to NL), the French National Research Agency (ANR Fluohyb ANR-17-CE09-0020). The authors thank CINA staff A.Ranguis for AFM measurements, D.Chaudanson and A.Altiè for electron microscopy.

## References

- 1 K. S. Yook and J. Y. Lee, *Adv. Mater.*, 2014, **26**, 4218–4233.
- 2 D. Ma, T. Tsuboi, Y. Qiu and L. Duan, *Adv. Mater.*, 2017, **29**, 1603253.
- 3 Y. Liu, C. Li, Z. Ren, S. Yan and M. R. Bryce, *Nat. Rev. Mater.*, 2018, **3**, 18020.
- 4 M. Y. Wong and E. Zysman-Colman, *Adv. Mater.*, 2017, **29**, 1605444.
- 5 N. Armaroli and H. J. Bolink, *Photoluminescent Materials and Electroluminescent Devices*, Springer International Publishing, Cham, 2017.
- 6 H. Peng, X. Sun, W. Weng and X. Fang, *Polymer materials for energy and electronic applications.*, Academic Press, 2016.
- 7 B. S. Mashford, M. Stevenson, Z. Popovic, C. Hamilton, Z. Zhou, C. Breen, J. Steckel, V. Bulovic, M. Bawendi, S. Coe-Sullivan and P. T. Kazlas, *Nat. Photonics*, 2013, **7**, 407–412.
- 8 T. A. Lin, T. Chatterjee, W. L. Tsai, W. K. Lee, M. J. Wu, M. Jiao, K. C. Pan, C. L. Yi, C. L. Chung, K. T. Wong and C. C. Wu, *Adv. Mater.*, 2016, **28**, 6976–6983.
- 9 I. S. Park, K. Matsuo, N. Aizawa and T. Yasuda, *Adv. Funct. Mater.*, 2018, **28**, 1802031.
- 10 T.-L. Wu, M.-J. Huang, C.-C. Lin, P.-Y. Huang, T.-Y. Chou, R.-W. Chen-Cheng, H.-W. Lin, R.-S. Liu and C.-H. Cheng, *Nat. Photonics*, 2018, **12**, 235–240.
- 11 Q. Zhang, H. Kuwabara, W. J. Potscavage, S. Huang, Y. Hatae, T. Shibata and C. Adachi, *J. Am. Chem. Soc.*, 2014, **136**, 18070–18081.
- 12 J.-X. Chen, K. Wang, C.-J. Zheng, M. Zhang, Y.-Z. Shi, S.-L. Tao, H. Lin, W. Liu, W.-W. Tao, X.-M. Ou and X.-H. Zhang, *Adv. Sci.*, 2018, **5**, 1800436.
- 13 W.-P. To, D. Zhou, G. S. M. Tong, G. Cheng, C. Yang and C.-M. Che, *Angew. Chemie*, 2017, **129**, 14224–14229.
- 14 T. Huang, W. Jiang and L. Duan, *J. Mater. Chem. C*, 2018, **6**, 5577–5596.
- 15 T. Chatterjee and K.-T. Wong, *Adv. Opt. Mater.*, 2019, **7**, 1800565.
- 16 J.-R. Gong, L.-J. Wan, S.-B. Lei, C.-L. Bai, X.-H. Zhang and S.-T. Lee, *J. Phys. Chem. B*, 2005, **109**, 1675–1682.
- 17 J. Y. Lee, J. Kim, H. Kim and M. C. Suh, *ACS Appl. Mater. Interfaces*, 2020, **12**, 23244–23251.
- 18 D. Liu, M. Zhang, H. Chen, D. Ma, W. Tian, K. Sun, W. Jiang and Y. Sun, *J. Mater. Chem. C*, 2021, **9**, 1221–1227.
- 19 P. L. dos Santos, J. S. Ward, M. R. Bryce and A. P. Monkman, *J. Phys. Chem. Lett.*, 2016, **7**, 3341–3346.
- 20 J. Phelipot, N. Ledos, T. Dombrey, M. P. Duffy, M. Denis, T. Wang, Y. Didane, M. Gaceur, Q. Bao, X. Liu, M. Fahlman, P. Delugas, A. Mattoni, D. Tondelier, B. Geffroy, P. Bouit, O. Margeat, J. Ackermann and M. Hissler, *Adv. Mater. Technol.*, 2021, **2100876**, 2100876.
- 21 D. Klintuch, M. V. Höfler, T. Wissel, C. Bruhn, T. Gutmann and R. Pietschnig, *Inorg. Chem.*, 2021, **60**, 14263–14274.
- 22 J. Kuno, N. Ledos, P. Bouit, T. Kawai and M. Hissler, *Chem. Mater.*, 2022, **In press**, <https://doi.org/10.1021/acs.chemmater.2c01994>.
- 23 J. Moreau, U. Giovanella, J.-P. Bombenger, W. Porzio, V. Vohra, L. Spadacini, G. Di Silvestro, L. Barba, G. Arrighetti, S. Destri, M. Pasini, M. Saba, F. Quochi, A. Mura, G. Bongiovanni, M. Fiorini, M. Uslenghi and C. Botta, *ChemPhysChem*, 2009, **10**, 647–653.
- 24 M. Zhu, Y. Li, C. Li, C. Zhong, C. Yang, H. Wu, J. Qin and Y. Cao, *J. Mater. Chem.*, 2012, **22**, 11128.
- 25 H. Tang, Y. Li, B. Chen, H. Wu, W. Yang and Y. Cao, *Opt. Mater. (Amst.)*, 2011, **33**, 1291–1296.
- 26 A. N. Aleshin, A. D. Sokolovskaya, I. P. Shcherbakov, P. N. Brunkov and V. P. Ulin, *Phys. Solid State*, 2013, **55**, 675–680.
- 27 B. H. Lessard, L. Beouch, F. Goubard, G. Wantz, M. Marić, D. Gigmes and F. Dumur, *Org. Electron.*, 2015, **17**, 377–385.
- 28 G. H. Michler, *Electron Microscopy of Polymers*, Springer Berlin Heidelberg, Berlin, Heidelberg, 2008.
- 29 D. V. Talapin, J.-S. Lee, M. V. Kovalenko and E. V. Shevchenko, *Chem. Rev.*, 2010, **110**, 389–458.
- 30 B. K. Gupta, G. Kedawat, P. Kumar, M. A. Rafiee, P. Tyagi, R. Srivastava and P. M. Ajayan, *J. Mater. Chem. C*, 2015, **3**, 2568–2574.
- 31 J. C. de Mello, H. F. Wittmann and R. H. Friend, *Adv. Mater.*, 1997, **9**, 230–232.

# SUPPORTING INFORMATIONS

---

## Nanohybrids as a tool to control the dispersion of organic emitters in solution-processed electroluminescent layers

Jonathan Phelipot,<sup>a</sup> Payal Manzhi<sup>b,c</sup> Nicolas Ledos,<sup>d</sup> Denis Tondelier,<sup>c</sup> Bernard Geffroy,<sup>b,c</sup> Pierre-Antoine Bouit,<sup>d</sup> Jörg Ackermann,<sup>a</sup> Muriel Hissler,<sup>d,\*</sup> Olivier Margeat.<sup>a,\*</sup>

a. J. Phelipot, Dr. O. Margeat, Dr. J. Ackermann.

Aix Marseille Univ, CNRS, CINaM, Marseille, France.

E-mail: [olivier.margeat@univ-amu.fr](mailto:olivier.margeat@univ-amu.fr)

b. Dr. P. Manzhi, Dr. D. Tondelier, Dr. B. Geffroy.

Laboratoire de Physique des Interfaces et des Couches Minces (LPICM), CNRS, Ecole Polytechnique, IP Paris, Palaiseau Cedex, France.

c. Dr. P. Manzhi, Dr. B. Geffroy

Université Paris-Saclay, CEA, CNRS, NIMBE, LICSEN, 91191, Gif-sur-Yvette, France.

d. N. Ledos, Dr. P-A. Bouit, Prof. Dr. M. Hissler.

Univ Rennes, CNRS, ISCR - UMR 6226, F-35000 Rennes, France.

E-mail: [muriel.hissler@univ-rennes1.fr](mailto:muriel.hissler@univ-rennes1.fr)

---

## **Experimental Part**

### **Experimental Part - General**

All experiments were performed under an atmosphere of dry argon using standard Schlenk techniques. Commercially available reagents were used as received without further purification. The synthesis of the emitter L was done following the procedure from our previous work.<sup>1</sup> The ZnO nanocrystals were prepared as published elsewhere.<sup>2</sup> Solvents were freshly purified using MBRAUN SPS-800 drying columns. UV-Visible spectra were recorded at room temperature on a VARIAN Cary 5000 spectrophotometer. The UV-Vis emission and excitation spectra measurements were recorded on a FL 920 Edinburgh Instrument equipped with a Hamamatsu R5509-73 photomultiplier for the NIR domain (300-1700 nm) and corrected for the response of the photomultiplier. AFM measurements: the tip comes from Mikromasch referenced HQ - NSC15 / Al - BS, while the AFM comes from Digital Instruments (Bruker) Multimode SPM equipped with a type E scanner (XY = 10 μm, Z = 2.5 μm) and a Nanoscope IIIa controller. The software Gwyddion ensures the processing of collected data. Morphology roughness RMS (root mean square) is analyzed on Glass /ITO /PEDOT:PSS / active layer sample. The layers including nanohybrids were characterized by HR-TEM (JEOL 3010, acceleration voltage of 300 kV). Holey carbon coated copper grid were used. Sacrificial layer of spin-coated PEDOT:PSS on ITO substrate was used before deposition of the nanohybrids containing matrix (see main text). Layer thickness were measured using a profilometer type Dektak XTS (Bruker, Germany) equipped with a stylus of 2 μm radius.

### **LED fabrication – Methods**


The OLED devices were fabricated onto indium tin oxide (ITO) glass substrates purchased from Xin Yang Technology (90 nm thick, sheet resistance of 15 Ω/□). Prior to organic layer deposition, the ITO substrates were cleaned by sonication in a detergent solution, rinsed twice in de-ionized water and then in isopropanol solution and finally treated with UV-ozone during 15 minutes. The OLEDs stack is: Glass / ITO/ PEDOT:PSS/ Matrix including nanohybrids/ BCP/ Alq<sub>3</sub>/ LiF/ Al prepared in inert atmosphere (Ar-filled glovebox) with spin-coated PEDOT:PSS (40nm), following evaporation deposition (deposited at a rate of 0.2 nm/s under high vacuum of 10<sup>-7</sup> mbar) of the other layers: BCP, Alq<sub>3</sub> before a thin layer of lithium fluoride is used as

---


<sup>1</sup> J. Phelipot, N. Ledos, T. Dombay, M.P. Duffy, M. Denis, T. Wang, Y. Didane, M. Gaceur, Q. Bao, X. Liu, M. Fahlman, P. Delugas, A. Mattoni, D. Tondelier, B. Geffroy, P. Bouit, O. Margeat, J. Ackermann, M. Hissler, Highly Emissive Layers based on Organic/Inorganic Nanohybrids Using Aggregation Induced Emission Effect, *Adv. Mater. Technol.* 2100876 (2021) 2100876. <https://doi.org/10.1002/admt.202100876>.

<sup>2</sup> A.K. Diallo, M. Gaceur, N. Berton, O. Margeat, J. Ackermann, C. Videlot-Ackermann, Towards solution-processed ambipolar hybrid thin-film transistors based on ZnO nanoparticles and P3HT polymer, *Superlattices Microstruct.* 58 (2013) 144–153. <https://doi.org/10.1016/j.spmi.2013.03.012>.


electron injection layer sequentially capped with a 100 nm thick layer of aluminum as cathode. Polyvinylcarbazole (PVK) and an oxadiazole derivative (2-(4-tert-butylphenyl)-5-(4-biphenyl-yl)-1,3,4-oxadiazole) including nanohybrids as electroluminescent blends were spin coated at a speed of 4000 rpm for 45 seconds, the layers were then annealed on a hot plate at 150°C for 5 minutes. The active area of the devices defined by the Al cathode was 0.3 cm<sup>2</sup>. After deposition, all the measurements were performed at room temperature under ambient atmosphere with no further encapsulation of devices. The current–voltage–luminance (I–V–L) characteristics of the devices were measured with a regulated power supply (ACT100 Fontaine) combined with a multimeter (Keithley) and a 1 cm<sup>2</sup> area silicon calibrated photodiode (Hamamatsu). Electroluminescence (EL) spectra and chromaticity coordinates of the devices were recorded with a PR650 SpectraScan spectrophotometer, with a spectral resolution of 4 nm.




**Figure S1.** TEM images of the layers (a) **M:N<sub>5</sub>**, (b) **M:N<sub>5</sub>:OA**, (c) **M:N<sub>15</sub>** and (d) **M:N<sub>15</sub>:OA**.




**Figure S2.** TEM (a) and AFM (b) images of the layer  $M:N_{10}:OA_{0.4\%}$ . TEM (c) and AFM (d) images of the layer  $M:N_{10}:OA_{0.6\%}$ .



**Figure S3.** SEM image of a cross-section of the layer  $M:N_{10}:OA$  spin-coated on a substrate. The 50 nm thick layer is present above the dashed line, and the brighter spots within the layer are attributed to the homogeneously dispersed nanohybrids.




**Figure S4.** AFM images at 10x10 $\mu$ m scale of the layer (a) **M:N<sub>5</sub>**, (b) **M:N<sub>5</sub>:OA**, (c) **M:N<sub>15</sub>** and (d) **M:N<sub>15</sub>:OA**.




**Figure S5.** Absorption spectra of layers of **M:L**, **M:N<sub>10</sub>** and **M:N<sub>10</sub>:OA** deposited on glass substrate.

	Sample name	M:N <sub>10</sub> :OA $\gamma$
PLQY (%)	Y = OA (0.2% v/v)	35 $\pm$ 3
	Y = OA (0.4% v/v)	33 $\pm$ 3
	Y = OA (0.6% v/v)	35 $\pm$ 3

**Table S1.** Photoluminescence quantum yields for three amounts of OA in M:N<sub>10</sub>:OA layers.




**Figure S6.** Electroluminescent spectra measured at 50 mA·cm<sup>-2</sup> of ITO/PEDOT:PSS/M:OA/BCP/Alq<sub>3</sub>/LiF/Al devices (inset: photograph image of the device).



**Figure S7.** J-V curves for various thicknesses of the electroluminescent layer **M:N<sub>10</sub>:OA** in ITO/PEDOT:PSS/**M:N<sub>10</sub>:OA**/BCP/Alq<sub>3</sub>/LiF/Al devices.

<b>M:N<sub>10</sub>:OA</b> layer thickness (+/- 5nm)	40 nm	50 nm	65 nm	100 nm
Threshold voltage (V)	4.5	4	6	9
EQE (%)	0.72	0.71	0.34	0.38
Power efficiency (lm/W)	0.77	0.82	0.27	0.11
Luminance efficiency (cd/A)	2.05	1.84	1.32	0.67

**Table S2.** Device performances for various thicknesses of the electroluminescent layer **M:N<sub>10</sub>:OA** in ITO/PEDOT:PSS/**M:N<sub>10</sub>:OA**/BCP/Alq<sub>3</sub>/LiF/Al devices.



**Figure S8.** J-V curves for various amounts of OA in the electroluminescent layer **M:N<sub>10</sub>:OA** in ITO/PEDOT:PSS/**M:N<sub>10</sub>:OA**/BCP/Alq<sub>3</sub>/LiF/Al devices.

OA amount (%) in <b>M:N:OA</b>	0.05 % v/v	0.1 % v/v	0.2 % v/v	0.4 % v/v	0.6 % v/v
Threshold voltage (V)	6	6	4	6	7
EQE (%)	0.58	0.66	0.71	0.65	0.34
Power efficiency (lm/W)	0.36	0.56	0.82	0.61	0.27
Luminance efficiency (cd/A)	1.81	1.98	1.84	1.91	1.32

**Table S3.** Device performances for various amounts of OA in the electroluminescent layer **M:N<sub>10</sub>:OA** in ITO/PEDOT:PSS/**M:N<sub>10</sub>:OA**/BCP/Alq<sub>3</sub>/LiF/Al devices.